

## Solvent based Tectyl remover

Tectyl 150 can be used to remove cured Tectyl solvent based coating (after storage or shipment) from the protected object/substrate. Tectyl 150 can be used to remove uncured Tectyl solvent based coatings. Tectyl 150 can also be used as a degreaser for other purposes.

---

## Applications

### Surface Preparation

CorPro recommends a substrate temperature of 10 - 35 °C at the time of product application.

### Application

Tectyl 150 is formulated to be used as supplied. Stirring is generally not required. Application should take place in a well ventilated area. Tectyl 150 can be applied by spraying with a spray gun or by cloth in case of small areas. Let the product work for approximately 3 - 6 minutes before removing Tectyl 150 off by high pressure water, preferably hot water or steam, leaving a clean surface.

---

## Features & Benefits

### Excellent performance

Tectyl 150 gives an excellent clean surface coating and is highly economical in use.

### Easy to apply

Application can be done with a brush or cloth in case of small areas.

### Easy to use

Tectyl 150 is an easy-to-use product, which removes most solvent based Tectyl

### End result

Tectyl 150 leaves a clean and grease free substrate.

---

## Trusted since 1930

Since 1930, Tectyl™ protective coatings have been extending the operational life of cars, trucks, buses and other vehicles and equipment. The Tectyl name is synonymous with quality coatings that are easy to apply, long-lasting and easy to remove when no longer required.

For more information on Tectyl products, programs and services please visit [www.tectyleurope.com](http://www.tectyleurope.com).

## Health & Safety

This product is not likely to present any significant health or safety hazards when properly used in the recommended application and good standards of personal hygiene are maintained. Reference is made to the Safety Data Sheet (SDS) which is available on request via your local sales office or via the internet.

## Protect the environment

Comply with local regulations. Do not discharge into drains, soil or water.

## Typical Properties

Typical property characteristics are based on current production. Whilst future production will conform to Tectyl specifications, variations in these characteristics may occur.

Tectyl™ 150	
Flash Point	40°C PMCC
Density @ 20°C	0.78 kg/ltr
Application Temperature	10 – 35°C
Boiling Point	149°C
VOC Content ISO 11890–2 (10.4)	780 g/ltr
Protection Indoor Months Na	PASS
Protection Outdoor Months Na	PASS



<https://tectyleurope.com>

## Storage

Tectyl 150 is frost-resistant. Tectyl 150 should be stored at temperatures between 0 and +35 °C. Packaging with product should be protected from direct sunlight and heat. Under proper storage conditions Tectyl 150 is best before 60 months after production date.

## Caution

Adequate ventilation is required for cure and to ensure against formation of combustible liquid. The partially cured film should not be exposed to ignition sources such as flares, flames, sparks, excessive heat or torches. Refer to The Safety Data Sheet for additional handling and first aid information.

## State of the information

April 27, 2026

## Validity

This information only applies to products manufactured in the following regions: Europe