

Premium solvent based, corrosion preventive compound in aerosol

Tectyl Multipurpose Transparent is a solvent cutback, resin based, transparent, corrosion preventive. It has good water displacing properties and can be used as a versatile corrosion protective for a wide variety of applications on ferrous and non-ferrous metals: automotive, marine, household and Industrial like tools, chromium-plated parts (wheels of bicycles). **Tectyl Multipurpose Transparent** provides special protection to industrial and auto electrical wiring and contacts such as ignition coils, spark plugs wires and terminals. **Tectyl Multipurpose Transparent** cures to a hard, transparent and colorless film.

Approvals / Performance Levels

| Tectyl™ Multipurpose Transparent | |
|--|-----------------|
| Recommended Dry Film Thickness over metal profile | 50 µm |
| Humidity Humidity; 100 % RH; @ 40°C; ISO 6270-2 CH (Q-Panels, Type R, ASTM A1008) | min. 75 days |
| Protection Indoor (min. months) | min. 36 |
| Protection Outdoor (min. months) | min. 6 |

Applications

Surface Preparation

The maximum performance of **Tectyl Multipurpose Transparent** can be achieved only when the metal surfaces to be protected are clean, dry and free of rust, oil and mill scale. CorPro recommends a substrate temperature of 10-35 °C at the time of product application.

Application

Tectyl Multipurpose Transparent gives a maximum performance when it is sprayed at an ambient and product temperature of 10-25 °C. Shake the can well before use and spray at a distance of approximately 30 cm from the surface. **Tectyl Multipurpose Transparent** is fast drying, and this can cause 'pin-holing' when applied too thick at once. It is advised to spray one layer per pass, wait for 2 to 3 minutes and then spray another layer. Continue like this until the required film thickness has been obtained.

Features & Benefits

Superior Protection

At the recommended DFT **Tectyl Multipurpose Transparent** will protect against corrosion.

Processing

Tectyl Multipurpose Transparent is easy to apply and easy to remove, when no longer needed.

Non-conducting

The special nonconductive formulation makes **Tectyl Multipurpose Transparent** the ideal product to protect wiring in cars and industrial applications.

Economical

With a Dry Film Thickness of only 45 microns, **Tectyl Multipurpose Transparent** can protect a big surface with just a little amount of the product.

Trusted since 1930

Since 1930, Tectyl™ protective coatings have been extending the operational life of cars, trucks, buses and other vehicles and equipment. The Tectyl name is synonymous with quality coatings that are easy to apply, long-lasting and easy to remove when no longer required.

For more information on Tectyl products, programs and services please visit www.tectyleurope.com.

Health & Safety

This product is not likely to present any significant health or safety hazards when properly used in the recommended application and good standards of personal hygiene are maintained. Reference is made to the Safety Data Sheet (SDS) which is available on request via your local sales office.

Protect the environment

Comply with local regulations. Do not discharge into drains, soil or water.



Typical Properties

Typical property characteristics are based on current production. Whilst future production will conform to Tectyl specifications, variations in these characteristics may occur.

| Tectyl™ Multipurpose Transparent | |
|----------------------------------|------------------|
| Density @ 20°C | 0.9 kg/ltr |
| Storage Temperature | 10 - 35°C |
| Nature of Propellant | Propane / Butane |
| VOC Content ISO 11890-2 (10.4) | 591 g/ltr |

Storage

Tectyl Multipurpose Transparent should be stored at temperatures between 10-35 °C. Do not freeze **Tectyl Multipurpose Transparent**. Shake well before use. Under proper storage conditions **Tectyl Multipurpose Transparent** is best before 36 months after production date.

Caution

Adequate ventilation is required for cure and to ensure against formation of combustible liquid. The partially cured film should not be exposed to ignition sources such as flares, flames, sparks, excessive heat or torches. Refer to the Safety Data Sheet (SDS) for additional handling and first aid information.

Note

The addition of any product over or under this coating is not recommended. The use of additional coatings could result in chemical incompatibility, thus affecting the performance of this coating as stated in the Performance level section. If a primer, other than a CorPro recommended product is required, written authorization must be obtained from CorPro.

State of the information

April 27, 2026

Validity

This information only applies to products manufactured in the following regions: Europe



<https://tectyleurope.com>